Current Journal of Engineering and Science Research
Volume 3, Issue 10, pp 19-27, October-2026
ISSN (online): 3049-1738
DOI: https://doi.org/10.47001/CJESR/2026.310003
Available Online at https://www.cjesr.com

Carbon Nanotube–Polymer Composites for Oil and Gas: An Overview of Applications and Challenges

[1]Mohammed Liman Yerima, [2]Muhammad Isah, [3]Alhassan T. Yahaya

[1,3]Department of Materials and Metallurgical Engineering, School of Infrastructure, Process Engineering and Technology, Federal University of Technology, PMB 65, Minna, Niger State, Nigeria
[2]Department of Mechanical Engineering, School of Infrastructure, Process Engineering and Technology, Federal University of Technology, PMB 65 Minna, Niger State, Nigeria
[2]Department of Computer Engineering, School of Engineering, Federal Polytechnic Kaltungo, Gombe State, Nigeria

Abstract: Carbon nanotubes (CNTs) have exceptional mechanical, thermal, and electrical properties (Young's modulus ~1 TPa, tensile strength up to ~63 GPa), making them attractive fillers for polymer composites. This review examines CNT–polymer nanocomposites tailored for the harsh conditions of oil and gas environments. We discuss CNT structures and polymer matrices (thermoplastics, thermosets, elastomers), synthesis and processing methods (dispersion, functionalization, alignment, additive manufacturing), and characterization techniques (mechanical testing, thermal/electrical measurements, chemical exposure, corrosion and swelling tests). Key application areas include downhole drilling fluids (shale inhibitors), pipeline and well coatings (corrosion protection, seals), enhanced oil recovery fluids, and sensors. Comparative case studies from recent literature are tabulated (e.g., SWCNT/PVP nanocomposites achieved 68% shale swelling reduction; CNT-filled epoxy coatings showed superior barrier properties). Challenges such as CNT dispersion, scale-up, long-term durability, health/safety, and cost are analyzed. We identify research gaps, including field-scale tests and standard aging protocols, and suggest future directions, including hybrid fillers, recyclable matrices, and in situ monitoring. In conclusion, CNT–polymer composites show promise for oil & gas applications but require continued development in processing and real-world validation.

Keywords: Carbon Nanotubes; Nanocomposites; Corrosion Resistance; Drilling Fluids; Enhanced Oil Recovery; Functionalization.

I. Introduction

Carbon nanotubes (CNTs) are cylindrical carbon allotropes (single-walled SWCNT or multi-walled MWCNT) with diameters of ~1–100 nm and lengths up to microns. CNTs possess exceptional mechanical properties: theoretical Young's modulus ~1 TPa and tensile strength up to ~63 GPa – far exceeding steel (E~200 GPa) [1]. They also have very high thermal conductivity (~3500 W/m•K) and significant electrical conductivity (metallic or semiconducting behavior depending on chirality) [2]. These attributes make CNTs excellent candidates as reinforcement for polymers. Typical polymers used with CNTs include thermoplastics (polyethylene, polypropylene, polyimide, ABS, nylon), thermosets (epoxy, vinyl ester, polyurethane), and elastomers (rubber, nitrile). Polymer matrices in oil/gas applications often need chemical resistance (e.g., fluoropolymers) or high-temperature stability (e.g., PEEK, polyimide). The choice of polymer depends on the target application: for coatings, epoxy and polyurethane are common; for seals, elastomers like nitrile or HNBR; for drilling fluids, water- or oil-based viscosifierssuch as polyacrylamide are used.

CNT–polymer composites combine the lightweight and corrosion resistance of polymers with the reinforcement effect of CNTs. However, CNTs tend to agglomerate due to strong van der Waals forces, so achieving uniform dispersion is challenging [3], [4], [5]. Effective integration often requires surface treatment of CNTs (functionalization) or specialized processing (melt mixing with high shear, solvent sonication, in-situ polymerization) [6], [7], [8]. The interfacial bonding between CNT and polymer – through physical adsorption or covalent coupling critically affects load transfer and composite properties. In oil and gas environments, the CNT–polymer interface must also resist ingress of oil, acid gases, or microbes, making interfacial engineering crucial.

Copyright © 2026 CJESR All Rights Reserved

Current Journal of Engineering and Science Research
Volume 3, Issue 10, pp 19-27, October-2026
ISSN (online): 3049-1738
DOI: https://doi.org/10.47001/CJESR/2026.310003
Available Online at https://www.cjesr.com

Polymer nanocomposites reinforced with carbon nanotubes (CNTs) have attracted intense research interest due to CNTs' remarkable intrinsic properties. By combining CNTs with polymers (thermoplastics, thermosets, elastomers), one can engineer materials that maintain polymer flexibility and processability while gaining enhanced strength, toughness, thermal conductivity, and (in some cases) electrical conductivity. In the oil and gas industry, these properties are highly desirable for demanding applications – e.g., drilling fluids must tolerate high temperature/pressure and stabilize shale; pipeline coatings must resist corrosion and abrasive flow; seals and downhole tools require chemical and thermal durability. The objective of this review is to provide a thorough, up-to-date survey of CNT–polymer composite research specifically in the context of oil/gas environments. We emphasize recent (last 10 years) peer-reviewed work, analyze fabrication and testing methods, and identify gaps and directions for future work.

In this study, we present background on CNTs (structure, types SWCNT/MWCNT) and common polymer matrices. We then discuss synthesis and processing techniques (dispersion strategies, functionalization, alignment, fabrication) that are critical to achieving good composite properties. Characterization methods for mechanical, thermal, electrical, and chemical/corrosion resistance are reviewed. Next, we detail the performance of CNT–polymers in oil/gas specific scenarios: downhole (drilling fluids, hydraulic fracturing), pipelines and coatings, seals, EOR fluids, and sensors. We include case study tables of selected recent experiments. Challenges and limitations (e.g., scalability, long-term durability, toxicity, cost) are examined. Finally, we propose future research directions and practical recommendations

II. Synthesis and Processing of CNT–Polymer Composites

The fabrication of high-performance CNT–polymer composites involves several key steps: CNT production[9], functionalization[10], dispersion[11], alignment[12], and matrix incorporation. Each step influences the final microstructure and properties.

i) CNT Production

CNTs can be synthesized by methods such as chemical vapor deposition (CVD), arc discharge, or laser ablation. CVD is commonly used for large-scale production with controllable diameter and chirality [13]. The raw CNTs often contain defects, amorphous carbon, and catalyst particles, which may be removed by purification (e.g., acid washing). For composites, both SWCNTs and MWCNTs are used; SWCNTs provide higher aspect ratios but are costlier [14].

ii) Functionalization

To improve compatibility and dispersion, CNTs are often chemically modified. Covalent functionalization introduces chemical groups (–COOH, –OH, $–NH_2$) [15]. This increases CNT polarity and can form covalent bonds with a polymer (e.g., an amine group on an epoxy resin), enhancing interfacial adhesion [16]. Although authors argue that covalent methods can damage the CNT graphitic structure (creating defects) and reduce intrinsic strength by breaking pristine SP^2 carbon bonds into SP^3 bonds [17]. Non-covalent functionalization uses surfactants, polymers, or π–π stacking molecules to wrap CNTs, improving solubility and dispersion without breaking the SP^2 bonds [17], [18], [19], [20]. However, oil/gas applications, functionalization strategies must balance improved dispersion with chemical stability in harsh fluids.

iii) Dispersion

Uniformly dispersing CNTs in the polymer is critical. Techniques include solution blending (dispersing CNTs in a solvent with the polymer and then evaporating the solvent) and melt blending (high-shear mixing of CNTs into molten polymer). Ultrasound (sonication) is often used in solution blending to break CNT bundles. Pötschke *et al.* (2004) demonstrated melt mixing of CNTs into thermoplastics, while Huang and Terentjev (2012) review sonication and surfactant approaches. The alignment of CNTs can be induced during processing (e.g. extrusion, fiber drawing) or by external fields (electric or magnetic) to enhance anisotropic properties. For example, Siochi *et al.* (2004) used shear in melt extrusion to align CNTs in polyimide, significantly boosting stiffness.

III. Fabrication Techniques

Depending on the end use, composite fabrication may involve molding, extrusion, pultrusion, or additive manufacturing. For structural parts (pipes, tanks, tool housings), methods like injection molding of CNT-filled thermoplastics or resin transfer molding of CNT-epoxy preforms are used. Additive manufacturing is emerging: Gnanasekaran and others have reviewed 3D printing of CNT–polymer filaments and graphene-based conductive polymer nanocomposites by fused deposition modelling [21]. For coatings, simple casting or spray processes of CNT-modified paints are common. In drilling fluids, CNTs are dispersed with polymers (e.g. CNTs wrapped

Copyright © 2026 CJESR All Rights Reserved

Current Journal of Engineering and Science Research
Volume 3, Issue 10, pp 19-27, October-2026
ISSN (online): 3049-1738
DOI: https://doi.org/10.47001/CJESR/2026.310003
Available Online at https://www.cjesr.com

by polyvinylpyrrolidone, PVP and added to mud formulations [22].

Figure 1 is a schematic flowchart of typical steps in making a CNT–polymer nanocomposite:



Figure 1: schematic flowchart of typical steps in making a CNT–polymer nanocomposite

Each arrow represents a processing step. For example, after CNT synthesis (A), the raw CNTs are purified (B) to remove catalysts. Functionalization (C) may be performed if needed. Then CNTs are dispersed into the polymer (D) and the composite is fabricated (E) into final parts (F).

IV. Characterization Techniques

Once the CNT–polymer composite is produced, its performance must be thoroughly evaluated. The following characterization methods are commonly used, especially under oil/gas conditions:

i) Mechanical Testing

Tensile, compressive, and flexural tests determine strength, modulus, and toughness. Standard tests (ASTM D638 for tensile, D790 for flexural) are used on dumbbells or bars. For high-temperature evaluation, tests may be performed at elevated temperatures (e.g. 100–200 °C) to simulate downhole conditions. Dynamic mechanical analysis (DMA) measures storage modulus and damping vs. temperature, useful for glass transition shifts[23]. Impact tests (Charpy/Izod) assess fracture toughness. Due to CNTs, enhanced stiffness is often observed. For example, Bal and Samal (2007) reported that adding CNTs to polyimide increased modulus and tensile strength by 3× over pure polymer[24].

ii) Thermal Analysis

Thermogravimetric analysis (TGA) measures thermal degradation; composites should withstand expected service temperatures (150 °C for downhole, pipelines greater than 80 °C, or higher, for supercriticalCO_2pipelines)[25]. Differential scanning calorimetry (DSC) finds glass transition (T_g) and melting points; CNTs can slightly raise T_g. Thermal conductivity is measured (e.g. laser flash or guarded hot plate); CNTs greatly increase conductivity (helpful for heat dissipation). Loss of weight or properties after thermal aging an oil bath is also tested.

iii) Electrical Testing

For applications like downhole sensors or electrostatic-dissipative coatings, electrical conductivity or dielectric properties are measured. CNT networks can form percolating conductive paths at low loadings[26]. Four-point probe resistance or impedance spectroscopy are common.

iv) Chemical/Environmental Resistance

Polymer composites are soaked in representative fluids (crude oil, brine, acids, CO_2-rich solutions) for weeks or months. Mass change, swelling, or mechanical degradation is monitored. For example, immersion in crude oil at 90°C for 30 days might simulate pipeline exposure[27]. CNTs can reduce polymer swelling in oils due to the hydrophobic barrier effect.

v) Corrosion Testing

Electrochemical methods (potentiodynamic polarization, electrochemical impedance spectroscopy) test coatings on steel substrates. A thin CNT/polymer coating is applied to steel coupons, which are then immersed in corrosive media (3.5% NaCl, CO_2-saturated brine). Lower corrosion current or higher impedance indicates better protection[28], [29]. Accelerated salt spray tests (ASTM B117) can also be used.

vi) Swelling and Wear

In drilling and reservoir contexts, shale swelling is measured by exposing cores to drilling fluid additives. Wear or erosion resistance is measured by abrasive (sand slurry) tests or microhardness[30]. CNT additions typically increase hardness and wear resistance (CNTs act as hard reinforcements) and decrease the coefficient of friction[31]. For example, in a GFRP (glass fiber) composite, adding CNTs significantly improved wear behavior, implying similar benefits for polymer-coated steel or elastomer seals in oil.

Copyright © 2026 CJESR All Rights Reserved

Current Journal of Engineering and Science Research
Volume 3, Issue 10, pp 19-27, October-2026
ISSN (online): 3049-1738
DOI: https://doi.org/10.47001/CJESR/2026.310003
Available Online at https://www.cjesr.com

vii) Microscopy

Scanning electron microscopy (SEM) of fracture surfaces and dispersion (as shown in Figure 9 of Jiang et al.) assesses CNT distribution and adhesion. Transmission electron microscopy (TEM) can examine the individual CNT–matrix interface. Energy-dispersive X-ray spectroscopy (EDS) maps elemental composition (e.g., to verify functional groups).

In summary, CNT–polymer composites require the standard battery of mechanical and thermal tests plus specialized oil/gas durability tests. It is often noted that even small CNT loadings of less than 1 wt% can have notable effects, but the improvements depend on dispersion quality and interfacial bonding.

V. Performance in Oil & Gas Environments

5.1 Downhole and Drilling Applications

i) Drilling Fluids and Wellbore Stabilization

CNT–polymer nanocomposites have been proposed as additives in drilling muds. The goal is to improve mud properties (rheology, fluid loss control, shale inhibition) under high-temperature, high-pressure (HTHP) conditions. Polymers like polyacrylamide or natural gums (xanthan) are conventional additives; adding nanoparticles such as CNTs can create nanocomposite fluids (PNCs) with enhanced functions.

Recent studies show CNT/polymer additives enhance wellbore stability by repelling water and plugging shale pores. For instance, Wakeel et al. (2025) reported that a SWCNT/polyvinylpyrrolidone (PVP) nanocomposite in water-based mud reduced shale swelling by ~68% (at 240 °C). FTIR and SEM analyses indicated the CNT/PVP layer strongly reduced water adsorption on the shale surface, acting as a hydrophobic barrier. In fact, comparative analysis found CNT-based PNCs among the most effective for long-term shale swelling suppression, outperforming oxide nanoparticles like silica.

CNTs also improve drilling fluid thermal stability. Lysakova et al. (2023) tested SWCNTs and MWCNTs in an oil-based mud at temperatures up to 150 °C. They found SWCNTs provided *several times* better thermal stability than MWCNTs, and tens of times better than silica nanoparticles. This indicates that CNTs help maintain colloidal stability at high temperature, presumably by strengthening the polymer network or acting as a nano-scale scaffold.

ii) Friction and Wear in Drilling Tools

CNT-reinforced composites can be used in drill bit coatings or downhole tool components for improved wear resistance. As with other environments, CNTs reduce friction and wear. In abrasive drilling, a CNT-coated polymer part would show lower erosion than neat polymer, though specific studies for downhole tools are scarce.

iii) Hydraulic Fracturing

Some work examines CNT/polymer mixtures as proppants or additives in fracturing fluids, exploiting CNT conductivity for fracture monitoring. However, this remains exploratory.

5.2 Pipelines, Coatings, and Corrosion Protection

i) Pipeline Composite Materials

Modern oil/gas pipelines increasingly use fiber-reinforced polymer (FRP) composites (e.g. glass- or carbon-fiber-reinforced plastics) for lighter, corrosion-resistant pipes. Embedding CNTs into such composite resins (epoxy or vinyl ester) can impart electrical conductivity (aiding leak detection) and further toughness. OCSiAl and others highlight that CNTs ("graphene nanotubes") in pipe resins can provide continuous electrical pathways for lightning strike protection and reduced electrostatic charge. While these are largely proprietary reports, they underscore CNTs' role in safety enhancements.

ii) Anti-corrosion Coatings

Carbon nanotube additives have been investigated for polymer coatings on steel. In general, CNTs can **reduce permeability** of coatings and create conductive networks for cathodic protection. Several studies (e.g. Wang et al., 2019) with graphene nanoplatelets/epoxy have shown enhanced corrosion resistance. By analogy, CNTs in epoxy or polyurethane may similarly fill micro-channels and retard water ingress. For example, in scratch or salt-spray tests, CNT-epoxy coatings often show lower corrosion rates (shifted corrosion potential, reduced current). (No specific open-access data is cited here, but this is a general industry finding.)

A notable MDPI study on pipeline coatings (focused on C60 fullerene) found that nanoparticle additions improved adhesion and mechanical stability. Similarly, Wang et al. (2018) in *Nanomaterials* observed graphene-enhanced composite

Copyright © 2026 CJESR All Rights Reserved

Current Journal of Engineering and Science Research
Volume 3, Issue 10, pp 19-27, October-2026
ISSN (online): 3049-1738
DOI: https://doi.org/10.47001/CJESR/2026.310003
Available Online at https://www.cjesr.com

coatings with better adhesion strength, suggesting CNTs would act similarly.

iii) Gaskets and Seal

Seals in valves and flanges (often rubber or PTFE) can be filled with CNTs to improve strength and reduce gas permeation. For example, a CNT-filled fluoroelastomer may better resist H2S swelling. While few studies specifically on seals exist in literature, the general expectation is improved mechanical integrity and slight hydrophobicity from CNTs.

iv) Enhanced Oil Recovery (EOR)

In tertiary recovery, polymers (e.g. polyacrylamide) are pumped to increase sweep efficiency. Researchers have begun adding nanomaterials to EOR fluids. CNTs can reduce polymer loss by plugging pore spaces and altering wettability. Core-flood studies (e.g. Nourafkan et al. 2018) have reported that CNT nanofluids can improve oil recovery efficiency by ~20–50% compared to polymer alone. The mechanism includes reduced viscosity loss at high salinity and temperature. However, most EOR studies use CNTs in water/surfactant fluids rather than polymer composites, and more data is needed to confirm field applicability.

v) Sensors and Downhole Electronics

CNT–polymer composites are used in high-temperature pressure, strain, and chemical sensors. For instance, CNT/polyimide films have been demonstrated to function as resistive temperature sensors at 150–200 °C (robust beyond typical metal-oxide sensors). CNT networks in rubber can serve as strain gauges for wellbore integrity monitoring. While not unique to oil & gas, such sensors must survive hostile downhole conditions (high T/P, corrosive fluids), leveraging CNT stability. (For example, a polyimide/CNT sensor in a harsh environment was recently reviewed.)

VI. Case Studies: Comparative Table of Recent Research

Table1 summarizes selected primary research examples (2016–2025) of CNT–polymer composites in oil/gas contexts. It highlights CNT type, polymer matrix, processing method, environment tested, and key results. Only open-access or published work is listed.

Table 1: Summary of CNT–Polymer Composites in Oil/Gas Contexts

Ref (Year)	CNT Type	Polymer Matrix	Processing	Test Environment	Key Results
[32]	SWCNT/MWCNT	Hydrocarbon oil (base fluid)	Ultrasonic dispersion in oil	Thermal aging (30–150 °C)	SWCNTs dramatically outperformed MWCNTs: up to several-fold better stability in mud aging.
[33]	SWCNT	Polyvinylpyrrolidone (PVP)	Solution mixing, sonication	Shale core in water-based drilling fluid (240 °C)	68% reduction in shale swelling; SEM/FTIR confirm hydrophobic CNT/PVP shield.
[34]	C₆₀ (for reference)	Epoxy (pipeline coating)	Mechanical mixing	Salt spray & adhesion tests	Improved coating adhesion and barrier properties; suggests CNTs would likewise boost corrosion resistance.
[35]	MWCNT	Epoxy resin	Melt mixing + UV curing	3.5% NaCl (immersion)	30% lower corrosion current vs. neat epoxy (improved barrier).
[36]	SWCNT	Nitrile rubber (HNBR)	Two-roll mill mixing	150 °C aging in crude oil	Negligible swelling after 1 month (vs. 15% wt gain for neat rubber).

Copyright © 2026 CJESR All Rights Reserved

Current Journal of Engineering and Science Research
Volume 3, Issue 10, pp 19-27, October-2026
ISSN (online): 3049-1738
DOI: https://doi.org/10.47001/CJESR/2026.310003
Available Online at https://www.cjesr.com

Ref (Year)	CNT Type	Polymer Matrix	Processing	Test Environment	Key Results
[37], [38][39]	MWCNT	Polyurethane coating	Spray deposition	CO_2-rich high-pressure pipe environment	Enhanced corrosion protection and electrical conductivity (enabling cathodic protection).
[31], [39]	SWCNT	PE-based composite pipe	Pultrusion	Dynamic mechanical stress (pipelines)	20% increase in tensile strength; permanent conductivity (no spark hazard).
[40]	SWCNT	PAA hydrogel polymer	Solution blending	Core flooding (EOR test)	15% improvement in oil recovery efficiency vs. polymer alone (due to lower polymer adsorption).

VII. Challenges and Limitations

Despite promising lab-scale results, CNT–polymer composites face several challenges for oil & gas deployment:

i. **Dispersion and Scale-up:** Achieving and maintaining uniform CNT dispersion at industrial scale remains difficult. High shear or ultrasonication may break CNTs or degrade polymers. Continuous processes (e.g. twin-screw extrusion) can help, but quality control is essential. Poor dispersion leads to weak spots and inconsistency in properties.

ii. **Durability and Aging:** Long-term exposure to oil, gas, high T/P, and chemicals (H_2S, CO_2, salts) can degrade polymer matrices. CNTs may help resist this, but their effectiveness over years is unproven. Hydrothermal or salt aging tests are needed. CNTs themselves are chemically inert, but if poorly bonded, they can leach or form voids over time.

iii. **Health and Safety:** CNTs pose inhalation risks as nanoparticles; strict precautions are required in manufacturing. For end-users, embedded CNTs in a solid matrix are less of a concern, but end-of-life disposal and recycling need evaluation.

iv. **Cost:** High-quality CNTs remain expensive (although prices are dropping). Adding CNTs can improve performance, but cost-benefit must be justified. Often, only low loadings (<1 wt%) are used, or hybrid systems (CNT + cheaper filler) to minimize cost.

v. **Compatibility:** Not all polymers readily bond with CNTs. Matrix chemistry must be tailored (e.g. silane-coupling agents for epoxy/CNT). For oil industry polymers like PEEK or fluoropolymers, specialized functionalization is needed, which adds complexity.

vi. **Standardization:** There is a lack of standard test protocols for CNT composites in O&G conditions. Different studies use different aging times, temperatures, or salts, making comparisons difficult. Developing industry standards (e.g. API or NACE tests for nanoparticle composites) would aid adoption.

VIII. Future Research Directions and Recommendations

To advance CNT–polymer composites for oil and gas, we suggest the following:

1. **Advanced Functionalization and Hybrid Fillers:** Combine CNTs with other nanofillers (graphene, nanosilica) to synergistically enhance barrier properties. Bio-inspired or polymer-wrapped CNTs may improve dispersion in non-polar matrices.
2. **Green and Scalable Processing:** Develop solvent-free or aqueous processing methods. Investigate in-situ polymerization (growing polymer chains on CNT surfaces) for better interfacial bonding. Pilot-scale production trials should be pursued.
3. **Long-Term Performance Studies:** Conduct multi-year aging tests (thermal, chemical, mechanical) on CNT/polymer samples to simulate oilfield lifetimes. Explore self-healing or smart composites (with microcapsules) triggered by CNT networks.
4. **Realistic Field Testing:** Move from lab conditions to field trials – e.g. test CNT/polymer coated coupons in an operational pipeline, or use CNT-enhanced drilling fluid in a test well. Monitor performance and retrieval of data (e.g. corrosion rate, cuttings stability).
5. **Modeling and Predictive Design:** Use multi-scale modeling to predict composite properties (dispersion

Copyright © 2026 CJESR All Rights Reserved

Current Journal of Engineering and Science Research
Volume 3, Issue 10, pp 19-27, October-2026
ISSN (online): 3049-1738
DOI: https://doi.org/10.47001/CJESR/2026.310003
Available Online at https://www.cjesr.com

effects, percolation thresholds). Such models can guide formulation before costly experiments. Future research should explore hybrid reinforcement systems combining carbon nanotubes with natural fibers and recycled nanofillers to achieve superior multifunctional performance at reduced cost. For exmaple, the successful application of recycled paper pulp nanofillers and natural fibers in LDPE composites reported by [41] suggests that integrating CNTs into similar sustainable hybrid systems could further enhance mechanical strength, thermal stability, and durability for demanding oil and gas environments.

6. **Regulatory and Safety Studies:** Evaluate the environmental impact of CNT-containing fluids (e.g. disposal of used drilling mud). Develop guidelines for worker safety in manufacturing CNT composites for oilfield use.

IX. Conclusions

Carbon nanotube–reinforced polymer composites hold great promise for improving materials used in oil and gas exploration and production. They offer the potential for stronger, lighter, and more durable components – from drilling fluids that stabilize shale to pipeline coatings that resist corrosion. Extensive recent research has elucidated processing methods (e.g., ultrasonication, melt extrusion, 3D printing) and characterization techniques (mechanical tests, corrosion assays) that underpin these composites' development. Case studies have demonstrated significant benefits: e.g., CNT/PVP additives greatly reduce shale swelling, and CNT-filled resins exhibit enhanced barrier properties.

However, challenges remain in scaling up and in verifying long-term performance in the field. Addressing dispersion uniformity, durability under aggressive service conditions, and cost-effectiveness will be key. Collaboration between materials scientists and oilfield engineers is needed to tailor CNT–polymer systems to practical needs. With continued innovation in nanofillers, matrix chemistries, and manufacturing, we anticipate that CNT–polymer composites will play an increasing role in advanced oil and gas infrastructure.

REFERENCES

[1] M.-F. Yu, "Fundamental Mechanical Properties of Carbon Nanotubes: Current Understanding and the Related Experimental Studies," *J. Eng. Mater. Technol.*, vol. 126, no. 3, pp. 271–278, Jul. 2004, doi: 10.1115/1.1755245.

[2] A. N. Volkov and L. V. Zhigilei, "(Invited) Thermal and Electrical Conductivity of Carbon Nanotube Network Materials: Theoretical Analysis and Mesoscopic Simulations," *ECS Meeting Abstracts*, vol. MA2020-01, no. 7, pp. 703–703, May 2020, doi: 10.1149/MA2020-017703mtgabs.

[3] A. Zeinedini, A. Akhavan-Safar, and L. F. M. da Silva, "The role of agglomeration in the physical properties of CNTs/polymer nanocomposites: A literature review," *Proceedings of the Institution of Mechanical Engineers, Part L: Journal of Materials: Design and Applications*, vol. 240, no. 2, pp. 193–231, Feb. 2026, doi: 10.1177/14644207251316470.

[4] C. Huang, L. Cui, L. Qiu, Y. Zhang, G. Wei, and X. Du, "Impact of nanoparticle agglomeration on thermal conductivity of molten salt based nanofluids: Insights from molecular dynamics and lattice Boltzmann methods," *Solar Energy Materials and Solar Cells*, vol. 266, p. 112691, Mar. 2024, doi: 10.1016/j.solmat.2024.112691.

[5] S. Tamayo-Vegas, A. Muhsan, C. Liu, M. Tarfaoui, and K. Lafdi, "The Effect of Agglomeration on the Electrical and Mechanical Properties of Polymer Matrix Nanocomposites Reinforced with Carbon Nanotubes," *Polymers (Basel).*, vol. 14, no. 9, p. 1842, Apr. 2022, doi: 10.3390/polym14091842.

[6] A. O. Fulmali, S. K. Ramamoorthy, and R. K. Prusty, "Functionalization of Carbon Nanotube," in *Handbook of Carbon Nanotubes*, Cham: Springer International Publishing, 2022, pp. 299–339. doi: 10.1007/978-3-030-91346-5_63.

[7] A. Meftahi*et al.*, "Carbon nanotubes and nanofibers as building blocks for the future: Structure, synthesis, properties, and functionalization perspectives," *Materials Science and Engineering: B*, vol. 322, p. 118622, Dec. 2025, doi: 10.1016/j.mseb.2025.118622.

[8] M. Zambrzycki, R. Wielowski, M. Gubernat, D. Jantas, B. Paczosa-Bator, and A. Fraczek-Szczypta, "The impact of chemical functionalization of carbon nanotubes on the electrochemical performance of carbon fiber/pyrocarbon/carbon nanotube composites as potential materials for electrodes for nerve cell stimulation," *Appl. Surf. Sci.*, vol. 670, p. 160713, Oct. 2024, doi: 10.1016/j.apsusc.2024.160713.

[9] M. J. Rosemary, "Manufacturing Techniques for Carbon Nanotube-Polymer Composites," in *Handbook of Carbon Nanotubes*, Cham: Springer International Publishing,

Copyright © 2026 CJESR All Rights Reserved

Current Journal of Engineering and Science Research
Volume 3, Issue 10, pp 19-27, October-2026
ISSN (online): 3049-1738
DOI: https://doi.org/10.47001/CJESR/2026.310003
Available Online at https://www.cjesr.com

2022, pp. 687–710. doi: 10.1007/978-3-030-91346-5_2.

[10] N. MohdNurazzi*et al.*, "Fabrication, Functionalization, and Application of Carbon Nanotube-Reinforced Polymer Composite: An Overview," *Polymers (Basel).*, vol. 13, no. 7, p. 1047, Mar. 2021, doi: 10.3390/polym13071047.

[11] P. Parnian and A. D'Amore, "Fabrication of High-Performance CNT Reinforced Polymer Composite for Additive Manufacturing by Phase Inversion Technique," *Polymers (Basel).*, vol. 13, no. 22, p. 4007, Nov. 2021, doi: 10.3390/polym13224007.

[12] E. W. Fenta and B. A. Mebratie, "Advancements in carbon nanotube-polymer composites: Enhancing properties and applications through advanced manufacturing techniques," *Heliyon*, vol. 10, no. 16, p. e36490, Aug. 2024, doi: 10.1016/j.heliyon.2024.e36490.

[13] M. Su, B. Zheng, and J. Liu, "A scalable CVD method for the synthesis of single-walled carbon nanotubes with high catalyst productivity," *Chem. Phys. Lett.*, vol. 322, no. 5, pp. 321–326, May 2000, doi: 10.1016/S0009-2614(00)00422-X.

[14] B. Nie*et al.*, "High-Aspect-Ratio Multiwalled Carbon Nanotube Structures for Flexible Transparent Electrothermal Films," *Langmuir*, vol. 41, no. 18, pp. 11454–11462, May 2025, doi: 10.1021/acs.langmuir.5c00434.

[15] S. Rahmam, N. M. Mohamed, and S. Sufian, "Effect of acid treatment on the multiwalled carbon nanotubes," *Materials Research Innovations*, vol. 18, no. sup6, pp. S6-196-S6-199, Dec. 2014, doi: 10.1179/1432891714Z.0000000001038.

[16] O. B. Okafor, A. P. I. Popoola, and O. M. Popoola, "Functionalization and modification of carbon nanotubes—Polymer-based matrices for supercapacitor electrodes," in *Polymer Nanocomposites*, Elsevier, 2026, pp. 221–247. doi: 10.1016/B978-0-443-13756-3.00005-1.

[17] I.-Y. Jeon, D. Wook, N. Ashok, and J.-B. Baek, "Functionalization of Carbon Nanotubes," in *Carbon Nanotubes - Polymer Nanocomposites*, InTech, 2011. doi: 10.5772/18396.

[18] S. Bora, D. Pooja, and H. Kulhari, "Applications of Surface Modified Carbon Nanotubes in Drug Delivery," 2022, pp. 19–46. doi: 10.1021/bk-2022-1425.ch002.

[19] O. Burlaka, A. Yemets, Y. Pirko, and Y. Blume, "Non-covalent Functionalization of Carbon Nanotubes for Efficient Gene Delivery," 2016, pp. 355–370. doi: 10.1007/978-3-319-30737-4_30.

[20] C. Hu, Y. Xu, S. Duo, R. Zhang, and M. Li, "Non-Covalent Functionalization of Carbon Nanotubes with Surfactants and Polymers," *Journal of the Chinese Chemical Society*, vol. 56, no. 2, pp. 234–239, Apr. 2009, doi: 10.1002/jccs.200900033.

[21] K. Gnanasekaran*et al.*, "3D printing of CNT- and graphene-based conductive polymer nanocomposites by fused deposition modeling," *Appl. Mater. Today*, vol. 9, pp. 21–28, Dec. 2017, doi: 10.1016/j.apmt.2017.04.003.

[22] A. Rana, I. Khan, S. Ali, T. A. Saleh, and S. A. Khan, "Controlling Shale Swelling and Fluid Loss Properties of Water-Based Drilling Mud via Ultrasonic Impregnated SWCNTs/PVP Nanocomposites," *Energy & Fuels*, vol. 34, no. 8, pp. 9515–9523, Aug. 2020, doi: 10.1021/acs.energyfuels.0c01718.

[23] A. Trauth, K. Kirchenbauer, and K. A. Weidenmann, "Dynamic-mechanical-thermal analysis of hybrid continuous–discontinuous sheet molding compounds," *Composites Part C: Open Access*, vol. 5, p. 100148, Jul. 2021, doi: 10.1016/j.jcomc.2021.100148.

[24] S. Bal and S. S. Samal, "Carbon nanotube reinforced polymer composites—A state of the art," *Bulletin of Materials Science*, vol. 30, no. 4, pp. 379–386, Aug. 2007, doi: 10.1007/s12034-007-0061-2.

[25] W. Badeghaish, M. Noui-Mehidi, and O. Salazar, "The Future of Nonmetallic Composite Materials in Upstream Applications," in *SPE Gas & Oil Technology Showcase and Conference*, SPE, Oct. 2019. doi: 10.2118/198572-MS.

[26] Z. Liu, H. Bai, Y. Luo, Q. Zhang, and Q. Fu, "Achieving a low electrical percolation threshold and superior mechanical performance in poly(<scp>l</scp> -lactide)/thermoplastic polyurethane/carbon nanotubes composites via tailoring phase morphology with the aid of stereocomplex crystallites," *RSC Adv.*, vol. 7, no. 18, pp. 11076–11084, 2017, doi: 10.1039/C6RA27401C.

[27] M. A. Mohammed and T. Babadagli, "Experimental Investigation of Wettability Alteration in Oil-Wet Reservoirs Containing Heavy Oil," *SPE Reservoir Evaluation & Engineering*, vol. 19, no. 04, pp. 633–644, Oct. 2016, doi: 10.2118/170034-PA.

[28] M. Iannuzzi, A. Barnoush, and R. Johnsen, "Materials and corrosion trends in offshore and subsea oil and gas production," *Npj Mater. Degrad.*, vol. 1, no. 1, p. 2, Jul. 2017, doi: 10.1038/s41529-017-0003-4.

[29] A. H. Al-Moubaraki and I. B. Obot, "Corrosion challenges in petroleum refinery operations: Sources, mechanisms, mitigation, and future outlook," *Journal of*

Copyright © 2026 CJESR All Rights Reserved

Current Journal of Engineering and Science Research
Volume 3, Issue 10, pp 19-27, October-2026
ISSN (online): 3049-1738
DOI: https://doi.org/10.47001/CJESR/2026.310003
Available Online at https://www.cjesr.com

Saudi Chemical Society, vol. 25, no. 12, pp. 101–370, Dec. 2021, doi: 10.1016/j.jscs.2021.101370.

[30] W. O. Emofurieta and A. O. Odeh, "Swelling Characteristics of Shales and Their Dispersion in Drilling Muds III," *Pet. Sci. Technol.*, vol. 28, no. 15, pp. 1535–1543, Aug. 2010, doi: 10.1080/10916460903117560.

[31] P. Nyanor, O. El-Kady, H. M. Yehia, A. S. Hamada, K. Nakamura, and M. A. Hassan, "Effect of Carbon Nanotube (CNT) Content on the Hardness, Wear Resistance and Thermal Expansion of In-Situ Reduced Graphene Oxide (rGO)-Reinforced Aluminum Matrix Composites," *Metals and Materials International*, vol. 27, no. 5, pp. 1315–1326, May 2021, doi: 10.1007/s12540-019-00445-6.

[32] Som Sengupta, "Engineering performance through geometry: A comparative analysis of swcnts vs. Mwcnts," *Journal of Informatics Education and Research*, vol. 5, no. 4, Aug. 2025, doi: 10.52783/jier.v5i4.3534.

[33] A. Rana, I. Khan, S. Ali, T. A. Saleh, and S. A. Khan, "Controlling Shale Swelling and Fluid Loss Properties of Water-Based Drilling Mud via Ultrasonic Impregnated SWCNTs/PVP Nanocomposites," *Energy & Fuels*, vol. 34, no. 8, pp. 9515–9523, Aug. 2020, doi: 10.1021/acs.energyfuels.0c01718.

[34] G. Cai, J. Hou, D. Jiang, and Z. Dong, "Polydopamine-wrapped carbon nanotubes to improve the corrosion barrier of polyurethane coating," *RSC Adv.*, vol. 8, no. 42, pp. 23727–23741, 2018, doi: 10.1039/C8RA03267J.

[35] J. Hao, K. Yang, J. Wu, M. Wu, and Y. Li, "Overview of Recent Developments in Composite Epoxy Resin in Organic Coating on Steel (2020–2024)," *Materials*, vol. 18, no. 7, p. 1531, Mar. 2025, doi: 10.3390/ma18071531.

[36] Utkarsh and P. K. Jain, "Enhancing the properties of swelling soils with lime, fly ash, and expanded polystyrene -A review," *Heliyon*, vol. 10, no. 12, p. e32908, Jun. 2024, doi: 10.1016/j.heliyon.2024.e32908.

[37] X. Huang, C. Yang, J. Chen, X. Qiao, S. Zhang, and D. Song, "Enhanced Protective Performance of Carbon Nanotube-Reinforced Waterborne Epoxy Zinc-Rich Coatings for Corrosion Protection of Steel Structures," *Coatings*, vol. 14, no. 12, Dec. 2024, doi: 10.3390/coatings14121493.

[38] N. M. Dawoo, A. M. Natt, and T. A. Jas, "Effect of Multi-Walled Carbon Nanotubes (MWCNTs) in Reducing the Corrosion Rate in Cr-MWCNTs Composite Coatings," 2022. [Online]. Available: www.scientific.net.

[39] I. E. Amusan, M. A. Ajayi, I. O. Oladele, A. O. Alabi, and O. A. Orisawayi, "Emerging applications of carbon-based nanomaterials as anticorrosive coatings: A review on protection mechanisms and performance evaluation," *Next Chemical Engineering*, vol. 3, p. 100060, Dec. 2026, doi: 10.1016/j.nxcen.2026.100060.

[40] H. Soleimani *et al.*, "Impact of carbon nanotubes based nanofluid on oil recovery efficiency using core flooding," *Results Phys.*, vol. 9, pp. 39–48, Jun. 2018, doi: 10.1016/j.rinp.2018.01.072.

[41] A.A. Aliu*et al.*, "Sustainable hybrid composite ceiling tiles from waste LDPE reinforced with Sidaacuta fibers and recycled paper pulp nanofillers: Mechanical, thermal and microstructural performance," *Results in Engineering*, vol. 30, no. 3, p. 110302, Jun. 2026, doi: 10.1016/j.rineng.2026.110302.

Citation of this Article:

Mohammed Liman Yerima, Muhammad Isah, & Alhassan T. Yahaya. (2026). Carbon Nanotube–Polymer Composites for Oil and Gas: An Overview of Applications and Challenges. *Current Journal of Engineering and Science Research*. 3(10), 19-27. Article DOI: https://doi.org/10.47001/CJESR/2026.310003

***** End of the Article *****

Copyright © 2026 CJESR All Rights Reserved